



## **Fabric Installation**

- During the parking lot inspection by a BSM Inspector the area(s) which require fabric installation will be marked.
- The area(s) are cleaned completely free of debris and will be edged from any vegetation found.
- To ensure a smooth surface without any depressions a leveling course of surface asphalt is installed where necessary.
- The residual asphalt binder (tack Coat), is uniformly spray-applied at a nominal rate of 0.25 gallons per square yard and is performed using truck-mounted distribution equipment.
- Immediately following the binder application, the approved fabric or geo-textile is installed, using truck-mounted fabric roll equipment while the tack coat is still hot, being sure not to allow wrinkling or folding of the fabric.